

## METHOD OF PRODUCING FERRULE AND FERRULE

### Field of the Invention

The present invention relates to a method of  
5 producing a ferrule and a ferrule.

### Background of the Invention

A ferrule 1 for a multi-fiber connector as shown in  
Fig. 12, for example, has a flange 1b formed of a synthetic  
10 resin at the rear portion of a body 1a whose rear portion  
from nearly the center has a cylindrical shape, and an  
opening 1c formed in the center of the body 1a. The  
ferrule 1 has two pin holes 1d formed in the lengthwise  
direction for insertion of guide pins and a plurality of  
15 fiber holes 1e for insertion of optical fibers formed  
between the two pin holes 1d.

The ferrule 1 is assembled into an optical connector  
by inserting optical fibers into the fiber holes 1e from  
back, injecting an adhesive through the opening 1c to  
20 adhere the optical fibers into the fiber holes 1e, and  
sealing the opening 1c with the adhesive.

### SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention  
25 to provide a ferrule producing method and a ferrule which  
can prevent fiber holes from being bent at the time of  
molding and can form the fiber holes accurately.

To achieve the object, according to the present  
invention, a method of producing a ferrule having a  
30 plurality of fiber holes for insertion of optical fibers  
formed between two pin holes for insertion of guide pins,  
which comprises a step of injecting a synthetic resin in a  
mold for forming the ferrule while holding a plurality of

pins with a Young's modulus of  $(22 \text{ to } 59) \times 10^{10} \text{ N/m}^2$  for forming the fiber holes at two points separated by a distance of 1.5 to 4 mm in a lengthwise direction of the pins.

5 To achieve the object, a first ferrule according to the present invention, produced by the method as described above, comprises pin holes for insertion of guide pins; a plurality of fiber holes for insertion of optical fibers, formed between the pin holes; and an opening which  
10 communicates with the plurality of fiber holes and through which an adhesive for securely adhering the optical fibers in the fiber holes is injected.

To achieve the object, a second ferrule according to the present invention comprises plural groups of fiber  
15 holes for insertion of optical fibers formed at predetermined intervals, each group having a plurality of fiber holes. Each fiber hole has a guide hole portion and a minute hole portion whose inside diameter is smaller than that of the guide hole portion.

20 To achieve the object, a third ferrule according to the present invention, comprises plural groups of fiber holes for insertion of optical fibers formed at predetermined intervals, each group having a plurality of fiber holes. Each fiber hole has a guide hole portion and  
25 a minute hole portion whose inside diameter is smaller than that of the guide hole portion. The guide hole portion has a taper portion formed on a minute hole portion side in such a way that the taper portion is tapered toward the minute hole portion and has a length  $L_t$  set to  $1 \geq L_t/L_g \geq$   
30  $1/3$  where  $L_g$  is a total length of the guide hole portion.

To achieve the object, a fourth ferrule according to the present invention, comprises plural groups of fiber  
holes for insertion of optical fibers formed at

predetermined intervals, each group having a plurality of fiber holes. Each fiber hole has a guide hole portion and a minute hole portion whose inside diameter is smaller than that of the guide hole portion. The guide hole portion is  
 5 formed in such a way that the inside diameter thereof becomes smaller in a stepwise manner toward the minute hole portion.

To achieve the object, a fifth ferrule according to the present invention, comprises plural groups of fiber  
 10 holes for insertion of optical fibers formed at predetermined intervals, each group having a plurality of fiber holes. Each fiber hole has a guide hole portion and a minute hole portion whose inside diameter is smaller than that of the guide hole portion. The guide hole portion is  
 15 formed in such a way that the inside diameter thereof becomes smaller continuously toward the minute hole portion.

The above and other objects of the present invention and the features and advantages thereof will become more apparent from the following detailed description, taken in  
 20 conjunction with the accompanying drawings.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a perspective view showing a lower mold, a core and molding pins which are used in a ferrule producing  
 25 method according to the present invention;

Fig. 2 is a cross-sectional view showing a mold closed, which is used in the ferrule producing method according to the present invention;

Fig. 3 is a cross-sectional view taken along the line  
 30 C1-C1 in Fig. 2;

Fig. 4 is a cross-sectional view showing a modification of the core which is used in the ferrule producing method according to the present invention, with

100260 00709660

the mold closed;

Fig. 5 is a perspective view of a ferrule according to one example of the present invention, which is produced by using the core in Fig. 4;

5 Fig. 6 is a front view of positioning blocks which are used when the core in Fig. 4 is in use;

Fig. 7 is a perspective view relating to second and third ferrules according to the present invention;

10 Fig. 8 is a cross-sectional view showing the ferrule in Fig. 7 along a horizontal plane;

Fig. 9 is a model explanatory diagram showing the molding state of the ferrule in Fig. 7 along a horizontal plane;

15 Fig. 10 is a cross-sectional view of a fourth ferrule according to the present invention;

Fig. 11 is a cross-sectional view of a fifth ferrule according to the present invention; and

20 Fig. 12 is a perspective view of a ferrule which is produced by a conventional method and a first ferrule which is produced by the present invention.

(conventional)

#### DETAILED DESCRIPTION

25 A ferrule producing method and a ferrule according to a first embodiment of the present invention will now be described referring to Figs. 1 through 6.

30 According to the method of the present invention, a first ferrule of the present invention is produced by using a mold 10 having a core 5, molding pins 6, a lower mold 11 and an upper mold 15 as shown in Figs. 1 and 2. The method according to the present invention can be used to produce a conventional ferrule 1 shown in FIG. 12. Therefore, how to produce the ferrule 1 using the method according to the present invention will be described below.

5

10

15

holes 1d.

20

25

30

14. The recess 12c has the same shape as the recess 14a.

As shown in Figs. 1 and 3, the first positioning block 13 has V-shaped grooves 13a formed in the top surface on the right and left sides and V-shaped grooves 13b formed between the V-shaped grooves 13a. The molding pins 6 are to be placed in the V-shaped grooves 13a, and the molding pins 5b are to be placed in the V-shaped grooves 13b.

As shown in Fig. 1, the second positioning block 14 has the recess 14a formed in the center in the widthwise direction and V-shaped grooves 14b formed on both sides of the recess 14a. The body 5a of the core 5 is to be placed in the recess 14a, and the molding pins 6 are to be placed in the V-shaped grooves 14b.

The upper mold 15 has a base block 16, the first positioning block 17 and the second positioning block 18 and is constructed in approximately the same manner as the lower mold 11. To avoid their redundant description, therefore, similar symbols will be given to the corresponding members in the diagrams and the following description. It is to be noted however that the first positioning block 17 has recesses 17a, not V-shaped grooves, where the molding pins 6 are to be placed, and has no V-shaped grooves formed where the molding pins 5b are to be placed.

25        In producing the ferrule 1 using the mold 10, first, the core 5 and the two molding pins 6 are set in the lower mold 11 by using the first positioning block 13 and the second positioning block 14.

At this time, each molding pin 6 should be placed in the associated V-shaped groove 13a and V-shaped groove 14b. The body 5a of the core 5 is placed in the lower mold 11 using the recess 14a and the support block 12a, and the individual molding pins 5b are placed in the associated V-

shaped grooves 13b.

Next, the upper mold 15 is put over the lower mold 11 from the above to close the mold 10 as shown in Fig. 2. As a result, the lower mold 11 and the upper mold 15 form a cavity C (see Fig. 2) for molding the ferrule 1 and the grooves 12b and grooves (not shown) in the base block 16 form a passage for a synthetic resin at the position that corresponds to the side portions of the flange 1b. In the closed mold 10, one end of each molding pin 5b is held by the associated V-shaped groove 13b and the first positioning block 17 and the other end of each molding pin 5b is held by the second positioning blocks 14 and 18 via the body 5a of the core 5, as shown in Fig. 3.

Then, a molten synthetic resin, such as a polyphenylene sulfide (PPS) resin or epoxy resin, is injected into the cavity C through the resin passage. As a result, the ferrule 1 shown in Fig. 12 which corresponds in shape to the cavity C is molded. After a predetermined time passes, the mold 10 is opened and the molded ferrule 1 is removed.

The molten synthetic resin is injected into the cavity C under high pressure. As the molding pins 5b are formed of a metal having a Young's modulus of  $(22 \text{ to } 59) \times 10^{10} \text{ N/m}^2$  and have one ends held by the first positioning blocks 13 and 17 and the other held by the second positioning blocks 14 and 18 via the body 5a of the core 5 as shown in Fig. 2, the pressure injection of the synthetic resin at the molding time does not deform the molding pins 5b in the method of the present invention. Therefore, the method of the present invention does not bend the fiber holes and produces the ferrule 1 with a high precision of forming the fiber holes.

As apparent from the above, unlike an optical

T00260:00T09660

5

10

15

25

30



positioning holes 19a, each row containing four positioning holes 19b. The positioning holes 19b position the respective molding pins 7b.

Second to fifth ferrules that achieve the object of the present invention will be described with reference to Figs. 7 to 11.

A ferrule 20 shown in Figs. 7 and 8 relates to the second and third ferrules. The ferrule 20 has an insertion port 20a, a plurality of fiber holes 20b and pin holes 20c.

The insertion port 20a has the front side which communicates with the fiber holes 20b and the rear side which is open at the rear portion of the ferrule 20 and where a tape fiber 21 is inserted. The fiber holes 20b are arranged in two rows, one over the other at a predetermined interval. Individual optical fibers 21a of the tape fiber 21 inserted through the insertion port 20a are inserted into the respective fiber holes 20b. When the ferrule 20 is butt-jointed to another optical connector ferrule, positioning guide pins (not shown) are inserted in the pin holes 20c.

As shown in Figs. 7 and 8, the fiber holes 20b have guide grooves 20d provided on the rear side which guide the optical fibers 21a of the tape fiber 21 inserted through the insertion port 20a to the respective fiber holes 20b.

As shown in Fig. 8, each fiber hole 20b has a guide hole portion Hg and a minute hole portion Hf whose inside diameter is smaller than that of the guide hole portion Hg. The inside diameter of the guide hole portion Hg is set larger than the outside diameter of the optical fiber 21a to facilitate the insertion of the optical fiber 21a into the molded ferrule 20. The guide hole portion Hg has a taper portion Pt formed on the minute hole portion (Hf) side in such a way that the taper portion Pt is tapered

toward the minute hole portion Hf. The length, Lt, of the taper portion Pt of the guide hole portion Hg is set to  $1 \geq Lt/Lg \geq 1/3$  where Lg is the total length of the guide hole portion Hg.

5 With the taper portion Pt, the guide hole portion Hg can permit smooth insertion of the associated optical fiber 21a into the small-diameter minute hole portion Hf.

The ferrule 20 with the above-described structure is produced as follows. As shown in Fig. 9, molding pins 23  
10 for forming the fiber holes 20b and molding pins 24 for forming the pin holes 20c are placed in a cavity C formed by the mold. Then, the ferrule 20 is produced by transfer molding by which a thermosetting resin, such as an epoxy resin, is injected into the cavity C or injection molding  
15 by which a thermoplastic resin, such as polyphenylene sulfide (PPS), is injected into the cavity C.

As shown in Fig. 9, each of the molding pins 23 for forming the fiber holes 20b has a large-diameter portion 23a for forming the guide hole portion Hg, a small-diameter  
20 portion 23b for forming the minute hole portion Hf, and a tapered portion formed between the large-diameter portion 23a and the small-diameter portion 23b in association with the taper portion Pt. The length of the tapered portion is set to  $1 \geq Lt/Lg \geq 1/3$  to match with the length Lt of the  
25 taper portion Pt. At the time of molding the ferrule 20, the molding pins 23 are laid in the cavity C with their adjoining large-diameter portions 23a contacting one another.

Accordingly, the small-diameter portion 23b for  
30 forming the minute hole portion Hf is not in contact with the tapered portion, thus forming an extra clearance corresponding to the tapered portion as compared with the prior art.

100260 00109600

At the time of molding the ferrule 20, therefore, the resin flows into space S between the upper and lower rows of molding pins 23 through the clearances each corresponding to the tapered portion in addition to the clearances that are formed between the small-diameter portions 23b as indicated by arrows in Fig. 9. Therefore, the resin flows into the space S between the upper and lower rows of molding pins 23 and the other portion of the cavity C approximately at the same time without a delay. This prevents the molding pins 23 from being bent by the resin pressure. Therefore, the fiber holes of the molded ferrule are not curved and are formed with high precision.

At the time of producing the conventional ferrule that does not have the taper portions Pt of the length Lt, by way of contrast, the tapered portions corresponding to the taper portions Pt are not formed unlike in the present invention. At the time of producing the conventional ferrule, therefore, the resin does not flow into space S between the upper and lower rows of molding pins through the clearances corresponding to the tapered portions.

At the time of producing the conventional ferrule, therefore, the resin flows into the space S between the upper and lower rows of molding pins with a delay after flowing into the other portion of the cavity C. The flow of the resin therefore applies large external stress to the molding pins for forming the fiber holes. Particularly, with reference to Fig. 9, those molding pins 23 in the upper and lower rows of molding pins 23 which are located near the center in the layout direction are pressed and bent in the direction to come closer to each other (up and down direction in Fig. 9), resulting in unstable positioning. As a result, the molded ferrule has curved fiber holes, lowering the fiber-hole forming precision.

Although the resin is injected into the cavity C from the sides of the mold in Fig. 9, the same advantages are obtainable in producing the ferrule if the resin is injected from above.

5 An embodiment which relates to a fourth ferrule of the present invention will be described with reference to Fig. 10.

A ferrule 25 has an insertion port 25a, a plurality of fiber holes 25b and pin holes 25c.

10 The insertion port 25a has the front side which communicates with the fiber holes 25b and the rear side which is open at the rear portion of the ferrule 25 and where a tape fiber (not shown) is inserted.

The fiber holes 25b are arranged in two rows, one  
15 over the other at a predetermined interval. The individual optical fibers (not shown) of the tape fiber inserted through the insertion port 25a are inserted into the respective fiber holes 25b. The fiber holes 25b have guide grooves 25d provided on the rear side which guide  
20 associated optical fibers (not shown) inserted through the insertion port 25a to the respective fiber holes 25b.

As shown in Fig. 10, each fiber hole 25b has a guide hole portion Hg and a minute hole portion Hf whose inside diameter is smaller than that of the guide hole portion Hg.  
25 The guide hole portion Hg is formed in such a way that the inside diameter becomes smaller in two stages by a first taper portion Pt1 formed on the guide groove (25d) side. The guide hole portion Hg also has a second taper portion Pt2 formed between the first taper portion Pt1 and the  
30 minute hole portion Hf.

When the ferrule 25 is butt-jointed to another optical connect r ferrule, positioning guide pins (not shown) are inserted in the pin holes 25c.

09560100 095601

In molding the ferrule 25 with the above-described structure, a clearance (space) is produced to the left of the first taper portion Ptl in Fig. 10 between the adjoining ones of the molding pins that form the fiber  
 5 holes 25b and are laid in the cavity of the mold. At the time of molding the ferrule 25, therefore, the resin flows into the space between the upper and lower rows of molding pins through the clearance. Like the ferrule 20, the ferrule 25 ensures stable positioning of the molding pins  
 10 for forming the fiber holes 25b so that the fiber holes 25b are formed with a high accuracy.

An embodiment which relates to a fifth ferrule of the present invention will be described with reference to Fig. 11.

15 A ferrule 27 has an insertion port 27a, a plurality of fiber holes 27b and pin holes 27c.

The insertion port 27a has the front side which communicates with the fiber holes 27b and the rear side which is open at the rear portion of the ferrule 27 and  
 20 where a tape fiber (not shown) is inserted.

The fiber holes 27b are arranged in two rows, one over the other at a predetermined interval. The individual optical fibers (not shown) of the tape fiber inserted through the insertion port 27a are inserted into the  
 25 respective fiber holes 27b. The fiber holes 27b have guide grooves 27d provided on the rear side which guide the associated optical fibers (not shown) inserted through the insertion port 27a to the respective fiber holes 27b.

As shown in Fig. 11, each fiber hole 27b has a guide  
 30 hole portion Hg and a minute hole portion Hf whose inside diameter is smaller than that of the guide hole portion Hg. The guide hole portion Hg is tapered in such a way that the inside diameter becomes smaller continuously toward the

T00259-00T0960

When the ferrule 27 is butt-jointed to another optical connector ferrule, positioning guide pins (not shown) are inserted in the pin holes 27c.

The foregoing description of the first ferrule has discussed the method of producing a ferrule with a single row of four fiber holes or a ferrule with two rows of fiber holes, each row having four fiber holes. However, the number of fiber holes in each row in the first ferrule is not limited to four. It is needless to say that each of the first to fifth ferrules may have three or more rows of fiber holes.

The foregoing description of the first ferrule has discussed the method of producing a ferrule with a single row of four fiber holes or a ferrule with two rows of fiber holes, each row having four fiber holes. However, the number of fiber holes in each row in the first ferrule is not limited to four. It is needless to say that each of the first to fifth ferrules may have three or more rows of fiber holes.